


OLIDENIM ® BLUE CTG



FASTNESS PROPERTIES

CONCENTRATION	LIGHT	DRY CLEANING	CHLORINE	DRY HEAT FIXATION
40 g/Kg	7/8	5	5	5
4 g/Kg	7	4/5	5	5

Test methods

Light	Suntest blue scale
Dry cleaning	ISO 105-D01
Chlorine	ISO 105- E03
Dry heat fixation	180°C for 3 minutes