

OLIMPRINT YELLOW RWS

DESCRIPTION

Excellent light and weathering fastness, high dry clearing fastness, high thermo-stability, high PVC fastness

Standard concentration		1/25	1/12	1/6
Pigment concentration g/Kg		1	2	4
Light fastness (Xenon arc)ISO 105-B02		7-8	8	8
(CO) Light fastness (carbon arc)AATCC-TM - 16A 600h		4-5	4-5	4-5
(CO) Light Fastness High temperature 3 cycles		4-5	4-5	4-5
ISO 105-B06	6 cycles	4	4	4
(PES) Light Fastness High temperature		3-4	4	4
SAE J 1885 488Kj				
Weathering (artificial)ISO 105-B04	500 h	7-8	7-8	7-8
	1,000 h	7-8	7-8	7-8
Dry clearing (perchloroethylene)ISO 105-D01		4-5	4-5	4-5
Dry cleaning (perchloroethylene)M&S C5		5	5	5
Thermofix fastness	150 °C - 30 s	5	5	5
ISO 105-P01 PES/CO	180 °C - 30 s	4-5	5	5
	210 °C - 30 s	4-5	4-5	4-5
Hypochlorite 54016		3	3	3
	170 °C - 3 min	++	++	++
	200 °C - 1 min	++	++	++
Thermostability	170 °C - 3 min	++	++	++
	200 °C - 1 min	++	++	++
	170 °C - 3 min	++	++	++
	200 °C - 1 min	++	++	++
PVC fastness ISO 105-X10				
		F	staining	
		4-5	PVC	5

