

OLIDENIM ® GOLDEN YELLOW CT



FASTNESS PROPERTIES

CONCENTRATION	LIGHT	DRY CLEANING	CHLORINE	DRY HEAT FIXATION
40 g/Kg	7/8	4/5	5	5
4 g/Kg	4/5	4	5	5

Test methods

Light Suntest blue scale

Dry cleaning ISO 105-D01

Chlorine ISO 105- E03

Dry heat fixation 180°C for 3 minutes