

# OLIDENIM ® ORANGE CT

## FASTNESS PROPERTIES

CONCENTRATION	LIGHT	DRY CLEANING	CHLORINE	DRY HEAT FIXATION
40 g/Kg	6/7	4	5	4/5
4 g/Kg	3/4	3/4		4/5

### Test methods

Light	Suntest blue scale
Dry cleaning	ISO 105-D01
Chlorine	ISO 105- E03
Dry heat fixation	180°C for 3 minutes