

OLIMPRINT ORANGE RWS

DESCRIPTION

Excellent light and weathering fastness, high dry clearing fastness, high thermo-stability, high PVC fastness

Standard concentration		1/25	1/12	1/6		
Pigment concentration g/Kg		1	2	4		
Light fastness (Xenon arc)ISO 105-B02		7-8	7-8	8		
(CO) Light fastness (carbon arc)AATCC-TM - 16A 600h		4/5	4-5	4-5		
(CO) Light Fastness High temperature 3 cycles		4-5	4-5	4-5		
ISO 105-B06	6 cycles	4	4	4		
(PES) Light Fastness High temperature		3-4	4	4		
SAE J 1885 488Kj						
Weathering (artificial)ISO 105-B04	500 h	7-8	7-8	7-8		
	1,000 h	7	7	7		
Dry clearing (perchloroethylene)ISO 105-D01		5	5	5		
Dry cleaning (perchloroethylene)M&S C5		5	5	5		
Thermofix fastness	150 °C - 30 s	5	5	5		
	180 °C - 30 s	5	5	5		
	210 °C - 30 s	4-5	4-5	4-5		
Hypochlorite 54016		3	3	3		
Thermostability	170 °C - 3 min	CO	++	++	++	
	200 °C - 1 min		++	++	++	
	170 °C - 3 min	CO/PES	++	++	++	
	200 °C - 1 min		++	++	++	
	170 °C - 3 min	PES	++	++	++	
	200 °C - 1 min		++	++	++	
	PVC fastness ISO 105-X10		F		staining	
				4-5	4-5	PVC

