

## OLIMPRINT RED RWS/N

### DESCRIPTION

Excellent light and weathering fastness, high dry clearing fastness, high thermo-stability, high PVC fastness

Standard concentration		1/25	1/12	1/6	
Pigment concentration g/Kg		1	2	4	
Light fastness (Xenon arc)ISO 105-B02		7-8	7-8	8	
(CO) Light fastness (carbon arc)AATCC-TM - 16A 600h		4	4	4	
(CO) Light Fastness High temperature 3 cycles		4-5	4-5	4-5	
ISO 105-B06	6 cycles	3-4	3-4	3-4	
(PES) Light Fastness High temperature		4	4	4	
SAE J 1885 488Kj					
Weathering (artificial)ISO 105-B04	500 h	7-8	7-8	7-8	
	1,000 h	7-8	7-8	7-8	
Dry clearing (perchloroethylene)ISO 105-D01		4-5	4-5	4-5	
Dry cleaning (perchloroethylene)M&S C5		5	5	5	
Thermofix fastness	150 °C - 30 s	5	5	5	
	180 °C - 30 s	5	5	5	
	210 °C - 30 s	4-5	4-5	4-5	
Hypochlorite 54016		5	5	5	
Thermostability	170 °C - 3 min	CO	++	++	++
	200 °C - 1 min		++	++	++
	170 °C - 3 min	CO/PES	++	++	++
	200 °C - 1 min		++	++	++
	170 °C - 3 min	PES	++	++	++
	200 °C - 1 min		++	++	++
	PVC fastness ISO 105-X10			F	staining PVC
				4-5	4-5

